



Drill Assay Results for Silver

Prospect	Drillhole	East	North	From_m	To_m	Length_m	Ag g/t	Co_pct	Ag oz/t
Kerr #2	FCC-18-0023	601,550	5,247,508	102.3	107	4.7	88.0	0.27	2.8
Kerr #2	FCC-18-0032	601,883	5,247,722	88	92.0	4.1	168.8	0.27	5.4
Kerr	FCC-18-0055	601,390	5,247,711	85.7	87	1.3	613.1	1.61	19.6
Kerr	FCC-18-0058	601,501	5,247,774	29.4	33	3.6	820.6	0.45	26.3
Drummond	FCC-18-0093	601,806	5,247,945	172.1	174.3	2.2	515.1	0.61	16.5
Drummond	FCC-18-0094	601,693	5,247,725	20.0	22.0	2.0	450.6	0.10	14.4
Drummond	FCC-18-0095	601,708	5,247,820	24.0	26.8	2.8	179.7	0.56	5.8
Drummond	FCC-18-0106	601,721	5,247,766	31.0	39.5	8.5	125.5	0.03	4.0
	including			31.0	31.9	0.9	621.7	0.18	19.9
Crown Reserve	FCC-18-0174	601,209	5,247,697	66.0	68.5	2.5	1441.5	0.28	46.1
Keeley	KF-K3-0001	613,234	5,227,978	108.5	111.5	3.0	445.0	0.01	14.2
Keeley South	FCC-18-0045	612,983	5,227,781	150.1	151.4	1.3	785	0.01	25.1
Keeley South	KF-KD-0005	613,196	5,227,796	77.53	79.9	2.3	316	0.23	10.1

Note: Drilling widths do not represent true thickness of mineralization. Veins occur at several angles. Drilling is oriented perpendicular to the general structural trend of mineralization based on bedrock measurements and previous drilling. All drill core has been oriented using Boart-Longyear tools. Drill hole co-ordinates are given in UTM NAD83 Zone 17

First Cobalt has implemented a quality control program to comply with common industry best practices for sampling and analysis.

Geochemical data were received from AGAT Laboratories in Mississauga, Ontario, Canada (with the exception of hole FCC-18-0132, from which samples were sent to ALS Laboratories in Sudbury, Ontario, Canada). Sample preparation for AGAT was done in Timmins, Ontario, Canada. At the laboratory, samples <5 kg are dried and crushed to 75% passing 2 mm screen, a 250 g split are then taken and pulverised to 85% passing 75 microns for analysis. AGAT has used a sodium-peroxide fusion and ICP finish for analyses on all samples. High silver values (>20 g/t) are determined by a separate three-acid digestion and ICP finish. AGAT is a fully accredited laboratory and conforms with the requirements of CANP4E (ISO/IEC 17025:2005) and CANP1579 by the Standards Council of Canada. ALS using a four-acid digestion of samples followed by an ICP-AES and ICP-MS finish for 61 elements.

All results have passed internal QA/QC protocols.